trictive properties in response to electrical or mechanical fields. An example of an electrostrictive-grafted elastomer with a piezoelectric poly(vinylidene fluoride-trifluoro-ethylene) copolymer. This combination has the ability to produce a varied amount of ferroelectric-electrostrictive molecular composite systems. These may be operated as a piezoelectric sensor or even an electrostrictive actuator.

[0069] Materials suitable for use as an electroactive polymer may include any substantially insulating polymer or rubber (or combination thereof) that deforms in response to an electrostatic force or whose deformation results in a change in electric field. Exemplary materials suitable for use as a pre-strained polymer include silicone elastomers, acrylic elastomers, polyurethanes, thermoplastic elastomers, copolymers comprising PVDF, pressure-sensitive adhesives, fluoroelastomers, polymers comprising silicone and acrylic moieties, and the like. Polymers comprising silicone and acrylic moieties may include copolymers comprising silicone and acrylic moieties, polymer blends comprising a silicone elastomer and an acrylic elastomer, for example.

[0070] Materials used as an electroactive polymer may be selected based on one or more material properties such as a high electrical breakdown strength, a low modulus of elasticity—(for large or small deformations), a high dielectric constant, and the like. In one embodiment, the polymer is selected such that is has an elastic modulus at most about 100 MPa. In another embodiment, the polymer is selected such that is has a maximum actuation pressure between about 0.05 MPa and about 10 MPa, and preferably between about 0.3 MPa and about 3 MPa. In another embodiment, the polymer is selected such that is has a dielectric constant between about 2 and about 20, and preferably between about 2.5 and about 12. The present disclosure is not intended to be limited to these ranges. Ideally, materials with a higher dielectric constant than the ranges given above would be desirable if the materials had both a high dielectric constant and a high dielectric strength. In many cases, electroactive polymers may be fabricated and implemented as thin films. Thicknesses suitable for these thin films may be below 50 micrometers.

[0071] As electroactive polymers may deflect at high strains, electrodes attached to the polymers should also deflect without compromising mechanical or electrical performance. Generally, electrodes suitable for use may be of any shape and material provided that they are able to supply a suitable voltage to, or receive a suitable voltage from, an electroactive polymer. The voltage may be either constant or varying over time. In one embodiment, the electrodes adhere to a surface of the polymer. Electrodes adhering to the polymer are preferably compliant and conform to the changing shape of the polymer. Correspondingly, the present disclosure may include compliant electrodes that conform to the shape of an electroactive polymer to which they are attached. The electrodes may be only applied to a portion of an electroactive polymer and define an active area according to their geometry. Various types of electrodes suitable for use with the present disclosure include structured electrodes comprising metal traces and charge distribution layers, textured electrodes comprising varying out of plane dimensions, conductive greases such as carbon greases or silver greases, colloidal suspensions, high aspect ratio conductive materials such as carbon fibrils and carbon nanotubes, and mixtures of ionically conductive materials.

[0072] Materials used for electrodes of the present disclosure may vary. Suitable materials used in an electrode may include graphite, carbon black, colloidal suspensions, thin metals including silver and gold, silver filled and carbon filled gels and polymers, and ionically or electronically conductive polymers. It is understood that certain electrode materials may work well with particular polymers and may not work as well for others. By way of example, carbon fibrils work well with acrylic elastomer polymers while not as well with silicone polymers.

[0073] While the disclosure has been described with reference to an exemplary embodiment, it will be understood by those skilled in the art that various changes may be made and equivalents may be substituted for elements thereof without departing from the scope of the disclosure. In addition, many modifications may be made to adapt a particular situation or material to the teachings of the disclosure without departing from the essential scope thereof. Therefore, it is intended that the disclosure not be limited to the particular embodiment disclosed as the best mode contemplated for carrying out this disclosure, but that the disclosure will include all embodiments falling within the scope of the appended claims.

**1**. A vehicle window system, comprising:

a movable window slidably disposed within a stationary frame;

a seal assembly in sealing communication with the movable window, the seal assembly comprising a active material operative to change at least one attribute in response to an activation signal, wherein a seal force of the seal assembly against the window changes with a change in the at least one attribute of the active material;

an activation device in operative communication with the active material; and

a controller in operative communication with the activation device.

**2**. The vehicle window system of claim 1, wherein the active material comprises a shape memory alloy, a shape memory polymer, a ferromagnetic shape memory alloy, an electroactive polymer, an electrorheological fluid, a magnetorheological elastomer, a dielectric elastomer, a magnetorheological fluid, piezoelectric material, an ionic polymer metal composite, or combinations comprising at least one of the foregoing materials.

**3**. The vehicle window system of claim 1, wherein the active material forms an actuator, wherein the actuator is external to the seal assembly.

**4**. The vehicle window system of claim 1, wherein the movable window is in operative communication with a motor.

**5**. The vehicle window system of claim 1, wherein the movable window is in operative communication with a hand crank.

**6**. The vehicle window system of claim 1, wherein the seal assembly comprises a plurality of strips and/or wires of the active material embedded within a seal structure.

**7**. The vehicle window system of claim 1, wherein the seal assembly has a cross sectional area that selectively decreases or increases in response to the activation signal.