



US 20070179228A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2007/0179228 A1**

Yoshida et al. (43) **Pub. Date: Aug. 2, 2007**

(54) **ACRYLIC ELASTOMER COMPOSITION**

(30) **Foreign Application Priority Data**

(76) Inventors: **Tamotsu Yoshida**, Kitaibaraki city (JP);
Jun Okabe, Kitaibaraki city (JP)

May 14, 1998 (JP) 150745/1998

Publication Classification

Correspondence Address:

BUTZEL LONG
350 SOUTH MAIN STREET
SUITE 300
ANN ARBOR, MI 48104 (US)

(51) **Int. Cl.**
C08K 5/00 (2006.01)

(52) **U.S. Cl.** **524/284; 524/444**

(21) Appl. No.: **11/643,391**

(57) **ABSTRACT**

(22) Filed: **Dec. 21, 2006**

Related U.S. Application Data

(60) Division of application No. 10/693,686, filed on Oct. 24, 2003, now abandoned, which is a continuation of application No. 09/277,590, filed on Mar. 26, 1999, now abandoned.

An acrylic elastomer composition comprising (A) a halogen-containing acrylic elastomer, (B) a polyvalent carboxylic acid, (C) a quaternary onium salt and (D) a hydrotalcite can be vulcanized within a shorter vulcanization time to give a vulcanization product having distinguished normal state physical properties and compression set characteristics, even without any secondary vulcanization.