

logical (ER) compositions, magnetorheological (MR) compositions, dielectric elastomers, ionic polymer metal composites (IPMC), piezoelectric polymers, piezoelectric ceramics, various combinations of the foregoing materials, and the like.

[0036] Shape memory alloys (SMA's) generally refer to a group of metallic materials that demonstrate the ability to return to some previously defined shape or size when subjected to an appropriate thermal stimulus. Shape memory alloys are capable of undergoing phase transitions in which their yield strength, stiffness, dimension and/or shape are altered as a function of temperature. The term "yield strength" refers to the stress at which a material exhibits a specified deviation from proportionality of stress and strain. Generally, in the low temperature, or martensite phase, shape memory alloys can be plastically deformed and upon exposure to some higher temperature will transform to an austenite phase, or parent phase, returning to their shape prior to the deformation. Materials that exhibit this shape memory effect only upon heating are referred to as having one-way shape memory. Those materials that also exhibit shape memory upon re-cooling are referred to as having two-way shape memory behavior.

[0037] Shape memory alloys exist in several different temperature-dependent phases. The most commonly utilized of these phases are the so-called Martensite and Austenite phases discussed above. In the following discussion, the martensite phase generally refers to the more deformable, lower temperature phase whereas the austenite phase generally refers to the more rigid, higher temperature phase. When the shape memory alloy is in the martensite phase and is heated, it begins to change into the austenite phase. The temperature at which this phenomenon starts is often referred to as austenite start temperature (A_s). The temperature at which this phenomenon is complete is called the austenite finish temperature (A_f).

[0038] When the shape memory alloy is in the austenite phase and is cooled, it begins to change into the martensite phase, and the temperature at which this phenomenon starts is referred to as the martensite start temperature (M_s). The temperature at which austenite finishes transforming to martensite is called the martensite finish temperature (M_f). Generally, the shape memory alloys are softer and more easily deformable in their martensitic phase and are harder, stiffer, and/or more rigid in the austenitic phase. In view of the foregoing, a suitable activation signal for use with shape memory alloys is a thermal activation signal having a magnitude to cause transformations between the martensite and austenite phases.

[0039] Shape memory alloys can exhibit a one-way shape memory effect, an intrinsic two-way effect, or an extrinsic two-way shape memory effect depending on the alloy composition and processing history. Annealed shape memory alloys typically only exhibit the one-way shape memory effect. Sufficient heating subsequent to low-temperature deformation of the shape memory material will induce the martensite to austenite type transition, and the material will recover the original, annealed shape. Hence, one-way shape memory effects are only observed upon heating. Active materials comprising shape memory alloy compositions that exhibit one-way memory effects do not automatically reform, and will likely require an external mechanical force to reform the shape.

[0040] Intrinsic and extrinsic two-way shape memory materials are characterized by a shape transition both upon heating from the martensite phase to the austenite phase, as well as an additional shape transition upon cooling from the austenite phase back to the martensite phase. Active materials that exhibit an intrinsic shape memory effect are fabricated from a shape memory alloy composition that will cause the active materials to automatically reform themselves as a result of the above noted phase transformations. Intrinsic two-way shape memory behavior must be induced in the shape memory material through processing. Such procedures include extreme deformation of the material while in the martensite phase, heating-cooling under constraint or load, or surface modification such as laser annealing, polishing, or shot-peening. Once the material has been trained to exhibit the two-way shape memory effect, the shape change between the low and high temperature states is generally reversible and persists through a high number of thermal cycles. In contrast, active materials that exhibit the extrinsic two-way shape memory effects are composite or multi-component materials that combine a shape memory alloy composition that exhibits a one-way effect with another element that provides a restoring force to reform the original shape.

[0041] The temperature at which the shape memory alloy remembers its high temperature form when heated can be adjusted by slight changes in the composition of the alloy and through heat treatment. In nickel-titanium shape memory alloys, for instance, it can be changed from above about 100° C. to below about -100° C. The shape recovery process occurs over a range of just a few degrees and the start or finish of the transformation can be controlled to within a degree or two depending on the desired application and alloy composition. The mechanical properties of the shape memory alloy vary greatly over the temperature range spanning their transformation, typically providing the system with shape memory effects, superelastic effects, and high damping capacity.

[0042] Suitable shape memory alloy materials include, without limitation, nickel-titanium based alloys, indium-titanium based alloys, nickel-aluminum based alloys, nickel-gallium based alloys, copper based alloys (e.g., copper-zinc alloys, copper-aluminum alloys, copper-gold, and copper-tin alloys), gold-cadmium based alloys, silver-cadmium based alloys, indium-cadmium based alloys, manganese-copper based alloys, iron-platinum based alloys, iron-platinum based alloys, iron-palladium based alloys, and the like. The alloys can be binary, ternary, or any higher order so long as the alloy composition exhibits a shape memory effect, e.g., change in shape orientation, damping capacity, and the like.

[0043] Thus, for the purposes of this invention, it is appreciated that SMA's exhibit a modulus increase of 2.5 times and a dimensional change of up to 8% (depending on the amount of pre-strain) when heated above their Martensite to Austenite phase transition temperature. It is appreciated that thermally induced SMA phase changes are one-way so that a biasing force return mechanism (such as a spring) would be required to return the SMA to its starting configuration once the applied field is removed. Joule heating can be used to make the entire system electronically controllable. Stress induced phase changes in SMA are, however, two way by nature. Application of sufficient stress when an SMA is in its Austenitic phase will cause it to change to its lower modulus Martensitic phase in which it can exhibit up to 8% of "superelastic" deformation. Removal of the applied stress will cause the