ORGANIC SOLVENTS					
Acetone	100	70	(21)	24	None
Acetone	100		Boil	100	None
Amyl Alcohol	100	70	(21)	1000	None
Benzene	100	70	(21)	1000	None
Benzene	100	70	(21)	24	None
Carbon Tetrachloride	100	70	(21)	24	None
Carbon Tetrachloride	100		Boil	100	Moderate
Chlorothene	100	70	(21)	24	None
Dimethylformamide	100	70	(21)	24	None
Ethyl Ether	100	70	(21)	1000	None
Ethyl Alcohol	100	170	(77)	100	None
Ethylene Glycol/Water	50/50	210	(99)	1000	Moderate
Freon* 11	100	140	(60)	500	None
Freon 22	100	140	(60)	500	None
Jet Fuel (Texaco "Abjet" K-40)	100	70	(21)	24	None
Kerosene	100	140	(60)	500	None
Suva® Centri-LP (HCFC-123)	100	70	(21)	1000	None
Gasoline, Leaded	100	70	(21)	1000	None
Gasoline, Leaded	100	70	(21)	24	None
Methyl Alcohol	100	70	(21)	1000	None
Methylene Chloride	100	70	(21)	24	None
Methylene Ketone	100	70	(21)	24	None
Perchloroethylene	100	210	(99)	10	None
Toluene	100	70	(21)	24	None
Trichloroethylene	100	70	(21)	24	None

* None ..... 0 to 10% strength loss
Slight ..... 11 to 20% strength loss
Moderate ..... 21 to 40% strength loss
Appreciable ..... 41 to 80% strength loss
Degraded ..... 81 to 100% strength loss

Figura 4.4